

PRODUCT DATA SHEET

Sika AnchorFix®-1

FAST CURING ANCHORING ADHESIVE

DESCRIPTION

Solvent and styrene free based, two-component polyester anchoring adhesive.

USES

As a fast curing anchoring adhesive for all grades of:

- Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems
- Concrete
- Hollow and solid masonry
- Hard natural stone*
- Solid rock*
- * These substrates may vary greatly, in particular with regard to strength, composition and porosity. Therefore, for each application the suitability of Sika Anchor-Fix®-1 Adhesive must be tested by first applying Sika AnchorFix®-1 Adhesive only to a sample area. Check in particular bond strength, surface staining and discolouration.

CHARACTERISTICS / ADVANTAGES

- Fast curing
- Standard guns can be used
- Can be used at low temperatures
- High load capacity
- ETA Approval available
- Non-sag, even overhead
- Styrene-free
- Low odour
- Low wastage

APPROVALS / STANDARDS

- Injection system for use in masonry according to ETAG 029, ETA-12/0227, Declaration of Performance 020403010010000001 5034408, certified by notified product certification body 0679, certificate of constancy of performance 0679-DPD-0777, and provided with the CE marking
- Bonded injection type anchor for non cracked concrete according to ETAG 001 annex 1 and 5, ETA-13/0720, Declaration of Performance
 020403010010000001 5034408, certified by notified product certification body 1020, certificate of constancy of performance 1020-CPD-090-029816, and provided with the CE marking.

PRODUCT INFORMATION

ckaging	150 ml standard cartrid		20 cartridges p 12 cartridges p	
Colour	Component A:		white	
	Component B:		black	
	Component A+B mixed:		light grey	
elf Life	12 months from date of production All Sika AnchorFix®-1 cartridges have the expiry date printed on the label.			
orage Conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +25 °C. Protect from direct sunlight.			
ensity	~1.63 kg/l (component A+B mixed)			
ECHNICAL INFORMATION				
mpressive Strength	~60 N/mm² (7 days, +20 °C)			(ASTM D 695
odulus of Elasticity in Compression	~3 500 N/mm² (7 days, +20 °C)			(ASTM D 695
exural Strength	~28 N/mm² (7 days, +20 °C)			(ASTM D 790
nsile Strength	~12 N/mm² (7 days, +20 °C)			(ASTM D 638
odulus of Elasticity in Tension	~4 500 N/mm² (7 days, +20 °C)			(ASTM D 638
Thermal Resistance	Long term		+50 °C	
	Short term (1–2 hours) +8		+80 °C	
ass Transition Temperature	+60 °C			(DIN EN ISO 6721-1
PPLICATION INFORMATIO	N			
ixing Ratio	Component A : component B = 10 : 1 by volume			
yer Thickness	3 mm max.			
g Flow	Non-sag, even overhead			
oduct Temperature	Sika AnchorFix®-1 must be at a temperature of between +5 °C and +40 °C for application.			
nbient Air Temperature	-10 °C min. / +40 °C max.			
ew Point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.			
bstrate Temperature	-10 °C min. / +40 °C max.			
Curing Time	Temperature	Open time -		uring time - Tcur
	+30 °C	4 minutes		5 minutes
	+25 °C – +30 °C	4 minutes		0 minutes
	+20 °C – +25 °C	5 minutes	50	0 minutes
	+10 °C – +20 °C	6 minutes		5 minutes
	+5 °C – +10 °C	10 minutes		45 minutes
	+5 °C	18 minutes		45 minutes
	-10 °C ^{1 2}	30 minutes	24	4 hours
bstrate Temperature	Substrate temperature point. -10 °C min. / +40 °C ma Temperature +30 °C +25 °C - +30 °C +20 °C - +25 °C +10 °C - +20 °C +5 °C - +10 °C +5 °C	Open time - 4 minutes 4 minutes 5 minutes 6 minutes 10 minutes 18 minutes	Tgel C: 3: 40 5: 5: 6: 8! 14: 14: 14: 14: 14: 14: 14: 14: 14: 14:	uring ti 5 minut 0 minut 0 minut 5 minut 45 minut 45 minut





Minimum cartridge temperature: +5 °C
 This application is not covered by the scope of the product ETA or any other approval.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY


- Mortar and concrete must be at the required strength. No need to be 28 days old.
- Substrate strength (concrete, masonry, natural stone) must be verified.
- Pull-out tests must be carried out if the substrate strength is unknown.
- The anchor hole must always be clean, dry, free from oil and grease etc.
- Loose particles must be removed from the holes.
- Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.

MIXING


Getting the cartridge ready:




1. Unscrew the cap



2. Cut the film



3. Screw on the static mixer



4. Place the cartridge into the gun and start application

When the work is interrupted the static mixer can remain on the cartridge after the gun pressure has been relieved. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.




APPLICATION METHOD / TOOLS

Anchors in solid masonry / concrete




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.



The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)


Important: use oil-free compressors.



Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.




Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer.In any case avoid entrapping air. For deep holes extension tubing can be used.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.

Important: the anchor must be placed within the open time.




During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Thinner C. Wash hands and skin thoroughly with warm soap water.






Anchors in hollow blocks



Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor-and perforated sleeve size.

Note: with hollow material do not use rotary hammer drills.




The drill hole must be thoroughly cleaned with a round brush (brush at least 1x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned after each cleaning step with a blow pump or by compressed air, starting from the bottom of the hole (pump at least 1x).


Important: use oil-free compressors.



Insert perforated sleeve completely into the drill hole.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.



case avoid entrapping air.

Close the cap from the perforated sleeve to avoid some escape of the resin during entering the steel rod.



Insert the anchor with a rotary motion into the filled perforated sleeve. Use the adequate steel rod size.


Inject the adhesive into the perforated sleeve,

starting from the bottom,

while slowly drawing back

the static mixer. In any

Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Thinner C. Wash hands and skin thoroughly with warm soap water.

CLEANING OF TOOLS

Clean tools and application equipment with Sika® Thinner C immediately after use. Hardened / cured material can only be mechanically removed.

Product Data Sheet Sika AnchorFix®-1 June 2018, Version 01.01 020205010010000001



BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in

Sika (NZ) Limited

85-91 Patiki Road Avondale, Auckland 1026 New Zealand 0800 745 269 www.sika.co.nz





Product Data Sheet Sika AnchorFix®-1 June 2018, Version 01.01 020205010010000001 SikaAnchorFix-1-en-NZ-(06-2018)-1-1.pdf

